



PU


CHEMICAL RESISTANCE TABLE FOR PU GUMBOOTS



Dissolves




Poor
more than 30% change



Fair
16 - 30% change



Good
4 - 15% change



Excellent
0.3% change

Acetic Acid 3 n	3	Diesel Oil	5	Methyl Glycol	2
Acetone	2	Dimethyl Acetamide	1	Methyl Glycol Acetate	2
Aluminium Chloride 10% Sol.	4	Dimethyl Formamide	1	Methylene Chloride	2
Ammonia 3 n	5	Distilled Water	5	Mineral Oil	5
Ammonium Chloride 10% Sol.	5	Ethanol	3	Nitric Acid 3 n	1
Aniline	2	Ether	3	N-Methyl Pyrrolidone	1
ASTM-Fuel A	2	Ethyl Acetate	2	Ozone	5
ASTM-Fuel B	4	Ethylene Chloride	3	Paraffin Oil	5
ASTM-Fuel C	3	Ferric Chloride 10% Sol.	4	Perchlorethylene	2
ASTM-Oil 1	5	Formic Acid 3 n	2	Petroleum	5
ASTM-Oil 2	5	Freon 12	3	Petroleum Ether	5
ASTM-Oil 3	5	Freon 22	3	Phosphoric Acid 3 n	3
Benzene	2	Gear Box Oil SAE 90	5	Potassium Chloride 10% & 40% Sol.	5
Benzyl Alcohol	1	Glycerine	5	Potassium Dichromate 10% Sol.	5
Bleach	5	Glycol	5	Potassium Hydroxide 3 n	5
Brake Fluid ATE	5	Hydrochloric Acid 3 n	5	Potassium Nitrate	4
Brake Fluid ATS	5	Hydrogen Peroxide 3%	5	Potassium Permanganate 5% Sol.	2
Butane	4	Iso-Octane Fuel 1	5	Propane	4
Butyl Acetate	2	Iso-Octane 70%: 30% Toluene = Fuel 2	4	Pyridine	1
Butyl Alcohol	3	Iso-Octane 50%: 50% Toluene = Fuel 3	3	Sea Water (Technical)	5
Calcium Chloride 10% & 40% Sol.	5	Iso-Propanol	4	Sodium Bisulphate 10% Sol.	4
Carbon Disulphide	3	Kerosine	5	Sodium Chloride 10% Sol.	5
Carbon Tetrachloride	2	Lactic Acid 3 n	1	Sodium Hypochlorite Sol. PH 13.3	3
Caustic Soda Sol. 10%	5	Lubricating Grease: Calcium based	5	Sodium Sulphite	4
Chlorobenzene	2	: Lithium based	5	Sulphuric Acid 3 n	1
Chloroform	2	: Sodium based	5	Terpentine (Pine Oil)	4
Chromic Acid 3 n	2	Magnesium Chloride 10% & 30% Sol.	5	Tetrachlorethylene	2
Citronic Acid 3 n	4	Methane	4	Tetrahydrofuran	2
Cyclohexane	4	Methanol	4	Toluene	2
Cyclohexanon	2	Methyl Acetate	2	Trichloroethylene	2
Decalin	3	Methyl Ethyl Ketone	2	Xylene	2

If you are exposed to any of the acids, oils or chemicals that rate 1, 2 or 3 on the table we recommend a PVC gumboot.

The above table should be used as a general guide only. Performance in the actual working environment will depend upon the following: temperature of chemicals, concentrations of chemicals and duration of exposure.